MATERIAL DATA SAFETY SHEET

Issued in Australia by Bilby 3D Pty Ltd.

The attached Material Data Safety Sheet has been prepared by the manufacturer outside Australia.

In accordance with Australia WHS regulations the following Australian contact details apply

Section 1: AUSTRALIAN COMPANY DETAILS

In Australia the product is imported and distributed by:
Bilby 3D Pty Ltd
Mailing Address :
Kingsgrove Business Centre, 7/192 Kingsgrove Rd, Kingsgrove NSW 2208
Head Office Address :
Kingsgrove Business Centre, 7/192 Kingsgrove Rd, Kingsgrove NSW 2208
Contact Phone: 1800 847 333

Section 2: AUSTRALIAN EMERGENCY CONTACT

Emergency Contact
In the event of an emergency please contact:
Poisons Information Centre 24 hour Telephone Advice Line on 13 11 26

Section 3: AUSTRALIAN ISSUE DATA

Date of Issue : 1 March 2020

Technical Data Sheet: Firewire™ Flame Retardant ABS 3D Filament

Physical Properties	Standard	Unit	Typical Value
Density	ISO 1183	g/cc	1.18

Mechanical Properties	Standard	Unit	Typical Value
Tensile Strength, Break	ISO 527	MPa	45
Tensile Modulus	ISO 527	MPa	1990
Tensile Elongation, Break	ISO 527	%	4
Flexural Strength	ISO 178	MPa	80
Flexural Modulus	ISO 178	MPa	2250

Thermal Properties	Standard	Unit	Typical Value
Glass Transition Temperature (Tg)	DSC	°C	105
Deflection Temperature at 0.45 MPa (66psi)	ISO 75	°C	95

Fire Testing*	Standard	Unit	Typical Value
Flamability Rating (*Base Resin)	UL 94	-	V-0 @1.5mm

Printed Specimen Conditions
Printer: Open Source FDM/FFF
Nozzle: 0.4mm
Layer Height: 0.25mm
Infill: 100%, +/- 45°
Extrusion Temp: 235°C
Bed Temp: 110°C
Specimen Orientation: XY Flat

www.3dxtech.com